



SPECIFICATIONS: ASTM A615-GRADE 60  
 ROUND BAR: CARBON EQUIVALENT-.45% MAX.  
 YIELD STRENGTH-60 KSI MIN  
 TENSILE STRENGTH-90 KSI  
 ELONGATION-8"-18% MIN.  
 REDUCTION AREA- 30% MIN. (1/2" TO 2")  
 REDUCTION AREA- 22% MIN. (>2" TO 2 1/2")  
 REDUCTION AREA- 20% MIN. (>2 1/2" TO 3")

GALVANIZE: ASTM-A153, CLASS C

NUTS: ASTM A563-GR DH, ANSI B18.2.2

THREADS: UNIFIED NATIONAL COARSE  
 ANSI B1.1 CLASS 2A  
 THREADS ARE ROLLED OR CUT.

WASHERS: ASTM F-436

				REBAR- BENT GR 60		
				REVISION: A	P.O. COMPANY:	DRAWN BY: JEP
				DATE:	P.O. NUMBER:	CHECKED BY: AJS
				CONTRACTOR:		
				J. H. Botts LLC		
				DWG. NO.		
A	FOR RELEASE					
REV #	DESCRIPTION	DATE	BY			
REVISIONS						
				1 of 1		